



Tork Heavy-Duty Cloth Handy Box

Kleur: Wit Format: Folded



voordeel

- exelCLEAN voor meer efficiëntie bij het schoonmaken
- Multifunctioneel – de meeste oppervlakken in een veeg schoon
- Hoog absorptievermogen van vloeistoffen en olie
- Sterk genoeg voor het zwaardere reinigingswerk
- Goedgekeurd voor gebruik met voedingsmiddelen



producteigenschappen

artikel	systeem	Uitgevouwen lengte	Uitgevouwen breedte	Gevouwen lengte	Gevouwen breedte	Lagen	Kleur
530171	W7 - Handy box systeem	42.8 cm	38.5 cm	10.8 cm	38.5 cm	1	Wit



Tork Heavy-Duty Cloth Handy Box

Kleur: Wit Format: Folded

verzendgegevens

consumentenunit

EAN	7322540057560
stuks	200
hoogte	245 mm
breedte	239 mm
lengte	396 mm
volume	23.2 dm ³
nettogewicht	2637 g
brutogewicht	2967 g

transportunit

EAN	7322540057577
stuks	200
consumentenunits	1
materiaal	Carton
hoogte	245 mm
breedte	239 mm
lengte	396 mm
volume	23.2 dm ³
nettogewicht	2.6 kg
brutogewicht	3.0 kg

pallet

EAN	7322540275889
stuks	14000
consumentenunits	70
hoogte	1865 mm
breedte	800 mm
lengte	1200 mm
volume	1.6 m ³
nettogewicht	184.6 kg
brutogewicht	207.7 kg



Tork Heavy-Duty Cloth Handy Box

Kleur: Wit Format: Folded

milieu

Content

Chemical pulp, Polypropene, Polyester, Chemicals

Material

Chemical pulp Chemical pulp is produced either from softwood or hardwood. The wood chips are boiled together with chemicals and the major part of the lignin is removed. Chemical pulp is bleached in order to achieve a clean, bright and strong product, but also to increase the hygienic and absorbent qualities. There are two major bleaching methods: ECF (elementary chlorine free) and TCF (totally chlorine free). ECF is based on oxygene, chlorine dioxide and hydrogen peroxide. TCF is based on hydrogen peroxide and ozone. ECF is used in this product.

Polypropene Polypropene fibre is produced from polypropene resin. The resin is melted in an extruder and spun to fibres through spinnerettes and cooled with air. Fibres are then cut to intended fibre length. **Polyester** Polyester fibre is produced from terephtalic acid and ethyleneglycol, which react through condensation to polyester resin. The molten resin is spun to fibres through spinnerettes and cooled with air. Fibres are then cut to intended fibre length. **Chemicals** Both functional and process chemicals are used. The functional chemical used is wet strength agent. The wet strength agent is a polyamide (from polyamidine/epichlorhydrine polymer) with a very high affinity to the fibre. Process chemical used is a surfactant.

Production

This product is produced at Suameer mill, The Netherlands, and certified according to ISO 9001:2000, ISO 14001 and EMAS.

Destruction

This product is mainly used for industrial processes and hence it will be contaminated with different substances. This will determine how the used product will be destructed. The product itself is suitable for incineration. Contact local authorities before destruction.